


2019-02-05

DIN EN12390-3 Test on hardened concrete**Data**

Date : 2019-02-05
Recipe number StQ1
Production date 28.01.2019
Curing conditions water
Sample age 7 days
Testing date 4.02.2019
Weight 7,34
Kind of break standard

Specimen

Type : Cube
Side : 150 mm
Side : 150 mm
Side : 150 mm
Section : 22500 mm²

**Results**

Maximum load : P 1635,711335
Strength : R 72,698282 MPa


2019-02-05

DIN EN12390-3 Test on hardened concrete**Data**

Date : 2019-02-05
Recipe number StQ1
Production date 28.01.2019
Curing conditions water
Sample age 7 days
Testing date 4.02.2019
Weight 7,36
Kind of break standard

Specimen

Type : Cube
Side : 150 mm
Side : 150 mm
Side : 150 mm
Section : 22500 mm²

**Results**

Maximum load : P 1614,490863 kN
Strength : R 71,755149 MPa