

TECHNICAL DATA SHEET

HyDra Tex 5000 CS 0,2

Mechanically bonded composite, consisting of granulated bentonite, embedded and fixed between two layers of geo-textile and glued to a membrane.

Properties of geotextile	Test Method	Value
Carrier Layer - PP Woven	EN ISO 9864	100 g/m ²
Cover Layer - PP Nonwoven	EN ISO 9864	200 g/m ²
PE Membrane	EN ISO 9863-1	0,2 mm

Properties of bentonite	Test Method	Value
Montmorillonite Content	CUR 33	75% min
Swell Index	ASTM D 5890	24 ml/2 g min
Fluid Loss	ASTM D 5891	18 ml max
Moisture Content	DIN 18121-1	12% max

Properties of GCL	Test Method	Value
Thickness	EN ISO 9863	7,6 mm
Mass per unit area of bentonite	EN 14196	5000 g/m ²
Mass per unit area of GCL	EN 14196	5500 g/m ² (+/- 10%)
Tensile Strength MD	EN ISO 10319	10,4 kN/m (- 10%)
Tensile Strength CMD	EN ISO 10319	10,4 kN/m (- 10%)
Permeability	ASTM D 5887	NOT MEASURABLE
Index Flux	ASTM D 5887	NOT MEASURABLE
Peel adhesion to concrete	ASTM D 903 Mod	2,5 kN/m min
CBR Puncture Strength	EN ISO 12236	1,8 kN (- 10 %)
Peel Strength	ASTM D 6496	60 N/10cm (-10 %)

Standard Roll Dimensions	Test Method	Value
Width x Length	Typical	5,0 m. x 40 m.
Quantity	Typical	200 m ²

These data are average values derived from standard tests and are subject to usual product variation. The right is reserved to make changes without notice at any time.

REV 12SEP2016